

## SABIC® LLDPE R50035EE

### Linear low density polyethylene for Rotational moulding

#### Description.

SABIC® LLDPE R50035EE is a LLDPE copolymer that is designed to provide excellent stress crack resistance, excellent mechanical properties with high rigidity, toughness, gloss and very low warpage. The resin contains UV stabilizer. It is recommended that SABIC® LLDPE R50035EE is grinded before use in rotational moulding applications.

#### Typical Applications.

SABIC® LLDPE R50035EE is designed for rotational moulding of large industrial and agricultural tanks, trash containers and chemical shipping drums. Its excellent mechanical properties and low warpage makes it suitable for injection moulding applications such as screw closures, caps and housewares. SABIC® LLDPE R50035EE is UV stabilised; that provides excellent protection for the final product.

#### Processing conditions.

Oven temperature °C (°F) = 315 (600)

Typical processing temperature for injection moulding machines: 210 - 240 °C.

#### Mechanical properties.


Test specimens are prepared from compression moulded sheet made according to ASTM D-1928, procedure C.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

#### Typical data.

Revision 20100716

Properties	Units SI	Values	Test methods
<b>Polymer properties</b>			
<b>Melt flow rate (MFR)</b> at 190 °C and 2.16 kg	g/10 min	<b>5.0</b>	ASTM D 1238
<b>Density</b>	kg/m <sup>3</sup>	<b>935</b>	ASTM D 1505
<b>Mechanical properties</b>			
<b>Tensile test</b>			ASTM D 638
stress at yield	MPa	<b>16</b>	
stress at break	MPa	<b>17</b>	
strain at break	%	<b>590</b>	
<b>Flexural test</b>			ASTM D 790
Flexural strength	MPa	<b>13</b>	
Secant modulus at 1% elongation	MPa	<b>420</b>	
<b>Hardness Shore D</b>	-	<b>66</b>	ASTM D 2240
<b>ESCR (100% Igepal), F50</b>	h	<b>&gt;150</b>	ASTM D 1693B
<b>Thermal properties</b>			
<b>Vicat softening temperature</b>	°C	<b>114</b>	ASTM D 1525
<b>Brittleness temperature</b>	°C	<b>&lt;-75</b>	ASTM D 746



## SABIC® LLDPE R50035EE

### Linear low density polyethylene for Rotational moulding

**General information.** SABIC Europe's assortment contains both butene and hexene grades. SABIC® LLDPE, produced by gasphase technology, is characterized by a high purity, an excellent extrusion performance and draw down capability due to its low gel content. SABIC® LLDPE is stabilized with an antioxidant package suitable for film purposes.

**Health, Safety and Food Contact regulations.** Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet ([www.SABIC-europe.com](http://www.SABIC-europe.com)). Additional specific information can be requested via your local Sales Office.

**Quality.** SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO 9001-2000. It is SABIC Europe's policy to supply materials that meet customers specifications and needs and to keep up its reputation as a pre-eminent, reliable supplier of e.g. polyethylenes.

**Storage and handling.** Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

**Environment and recycling.** The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.